



检 测 报 告

Test Report

检测项目	抗菌防霉性能检测
Test Items	Antibacterial and Mildew-proof Test
委托单位	东莞强一木业有限公司
Applicant	Dongguan Qiangyi wood Co., LTD
检测类别	委托检测
Test Category	Entrusted Test
检测标准	JC/T 2039-2010
Test Standard	Antibacterial and Mildew-proof wooden boards for decoration
收样日期	2026-07-13
Sample Received	July 13 th , 2025

TEST REPORT DUPLICATION

This test report mustn't be reproduced, except in full, unless written permission by ICTT Lab.



注意事项

Notice Items

1. 未经授权批准的签名、验证人签名和批准人签名，本测试报告无效。

This test report is invalid without authorized approved signature, signature of verifier and approver.

2. 本测试报告如有补充、删减或更改即无效。

This test report is invalid if being supplemented, deleted or altered.

3. 除非另有说明，否则本报告中的观察结果和测试结果仅适用于所测试的样本。

Unless otherwise stated, the observations and test results in this report are relevant only to the sample(s) tested.

4. 对于测试报告的异议必须在收到报告后的 15 天内提交给 HJK。此报告并不意味着该材料、产品或服务目前或曾经处于 HJK 或 ICTT 的认证计划范围内。

Objections to the test report must be submitted to Hongjun within 15 days of report received date. This report does not imply that the material, product, or service is or have ever been under Hongjun or ICTT certification program.

5. 该测试申请人需确保样本信息的真实性，而这一真实性不需经 HJK 进行核实。

The test applicant is responsible for authenticity of sample information which not subject to verification of Hongjun.

6. 该测试适用的决策规则为：IEC 115:2007 指南中的程序 2 - 准确性方法，不受测量不确定度的影响。

The applicable decision rules of this test are: IEC Guide 115:2007 Procedure 2 - Accuracy method, do not subject to measurement uncertainty.

TEST REPORT DUPLICATION

This test report mustn't be reproduced, except in full, unless written permission by ICTT Lab.



Shanghai Hongjun Science & Technology Co., Ltd.

Family member of ICTT Cor

Add: 3rd and 4th Floor, Building 2, No. 598 Guanghua Road, Minhang District, Shanghai

Tel: 86-23-63525678

Fax: 86-23-63530958

Website: www.icctglobal.org

Report No.: HJ-RD-26150

Issue Date: Jul. 13th, 2026

检测报告

TEST REPORT

样 品 名 称 Sample Name	糯米胶多功能板	生 产 批 号 Serial No.	/
样 品 状 态 Sample Condition	样品完好，适合检验	型 号 Type	厚度 18mm
生 产 单 位 Manufacturer	东莞强一木业有限公司		
样 品 规 格 Sample Spec.	5cm×5cm	样 品 数 量 Sample Quantity	18 片
委 托 单 位 Client	东莞强一木业有限公司		
委 托 日 期 Consigned Date	2026.05.09	委 托 人 Consignor	/
样 品 编 号 Sample No.	QB-20260629-358N	检 测 类 别 Test Category	委托检测
检测项目 Test Item	抗细菌率，防霉菌等级		
室内环境条件 Room Condition	温度/Temperature: 23 °C	相对湿度/Relative Humidity: 63% RH	
检测依据 Test Standard	JC/T 2039-2010;		
检 测 结 论 Test Conclusion			
经检测，所检结果详见后页；			
（检测专用章）			
签发日期：2026 年 7 月 13 日			
Lssuing Date: July 13,2026			
备注 Remark	样品信息由委托单位提供，本公司检测结果仅对来样负责。		

Reporter: Jasmine Hu

Verifier: Tina. Deng

Approver: 

TEST REPORT DUPLICATION

This test report mustn't be reproduced, except in full, unless written permission by ICTT Lab.



检测报告

TEST REPORT

序 号 No.	检 测 项 目 Test Item	单 位 Unit	检 测 结 果 Test Result	备 注 Remark
1.	抗细菌率	%	>99	JC/T 2039-2010
2.	防霉等级	级	0	JC/T 2039-2010
抗细菌率		空白对照样品 24h 后平均回收菌数：1.7×10 ⁶ （cfu/片）		
		抗菌涂料试样 24h 后平均回收菌数：<50（cfu/片）		
		测试微生物：大肠杆菌 AS1.90		
防霉等级		评级标准： 0 级—不长； 1 级—长霉面积小于 10%； 2 级—霉菌生长覆盖面为 10%~30%； 3 级—霉菌生长覆盖面 30%~60%； 4 级—霉菌生长覆盖面大于 60%。		
		试验菌种： 黑曲霉-AS3.3928，球毛壳霉-AS3.3601， 绳状青霉-AS3.3875，出芽短梗霉-AS3.837， 宛式拟青霉-AS3.4253，土曲霉-AS3.3935。		
- 以下空白 -				

报告结束

TEST REPORT DUPLICATION

This test report mustn't be reproduced, except in full, unless written permission by ICTT Lab.